



DATA SHEET

H-7

Ceramic Core Material

© 2015 Certech, Inc., a business within Morgan Advanced Materials			
Description		Physical Properties	
General core type with an intermediate particle size distribution and open pore structure for use in Equiax castings. Generally used for difficult to leach parts as		Modulus of rupture (4-point), psi	825
		Length shrinkage (mold-to-fired), %	0.4
well as aluminium castings where core removal is accomplished by water blast or a knockout operation.		Chord shrinkage (mold-to-fired), %	0.6
Major Chemistry		Thermal expansion coefficient (25 - 1000°C), ppm/°C	1.0
Silica (SiO ₂), %	98		
Other, %	2	Bulk density, g/cc	1.6
	2	Apparent density, g/cc	2.2
Trace Element Analysis		Porosity, %	28
Iron (Fe), ppm	< 900	Absorption, %	18
Bismuth (Bi), ppm	< 1	•	
Lead (Pb), ppm	< 25	Cristobalite content (after fire), %	3
Silver (Ag), ppm	< 25	Cristobalite content	10
Antimony (Sb), ppm	< 25	(after 15 min. at 1390°C), %	
		Leachability	100
Tin (Sn), ppm	< 25	(30% boiling KOH, 30 g sample, 30 min.), %	
Zinc (Zn), ppm	< 50	,,	
		Core – Metal Reaction Compatibility	
		Most nickel based and aluminium alloys.	

Please note that all values quoted are based on test pieces and may vary according to component design. These values are not guaranteed in anyway whatsoever and should only be treated as indicative and for guidance only. Jul. 28, 2015