

## DATA SHEET

# P-78

### Ceramic Core Material

© 2015 Certech, Inc., a business within Morgan Advanced Materials

#### Description

High silica core type with a very fine particle size distribution. Used for DS and SX applications with very thin cross sections.

#### Major Chemistry

Silica (SiO <sub>2</sub> ), %	97
Zircon (ZrSiO <sub>4</sub> ), %	2
Alumina (Al <sub>2</sub> O <sub>3</sub> ), %	1

#### Trace Element Analysis

Iron (Fe), ppm	< 900
Bismuth (Bi), ppm	< 1
Lead (Pb), ppm	< 25
Silver (Ag), ppm	< 25
Antimony (Sb), ppm	< 25
Tin (Sn), ppm	< 25
Zinc (Zn), ppm	< 50

#### Physical Properties

Modulus of rupture (4-point), psi	1750
Length shrinkage (mold-to-fired), %	1.3
Chord shrinkage (mold-to-fired), %	1.3
Thermal expansion coefficient (25 - 1000°C), ppm/°C	1.2
Bulk density, g/cc	1.6
Apparent density, g/cc	2.3
Porosity, %	29
Absorption, %	18
Cristobalite content (after fire), %	6
Cristobalite content (after 30 min. at 1530°C), %	71
Leachability (30% boiling KOH, 30 g sample, 15 min.), %	100

#### Core – Metal Reaction Compatibility

Most DS and SX alloys.

Please note that all values quoted are based on test pieces and may vary according to component design. These values are not guaranteed in anyway whatsoever and should only be treated as indicative and for guidance only. Aug. 12, 2015