



DATA SHEET

G-3

Ceramic Core Material

© 2015 Certech, Inc., a business within Morgan Advanced Materials			
Description		Physical Properties	
General core type with an intermediate particle size distribution for Equiax castings. Formulated to be used for large land-based type cores that require good stability at elevated temperatures and for chunky airfoil cores up to 30 inches long, 8 inches wide, and 1 inch thick.		Modulus of rupture (4-point), psi	1600
		Length shrinkage (mold-to-fired), %	0.6
		Chord shrinkage (mold-to-fired), %	0.8
Major Chemistry		Thermal expansion coefficient (25 - 1000°C), ppm/°C	1.5
Silica (SiO ₂), %	70	Bulk density, g/cc	1.9
Zircon (ZrSiO ₄), %	30	Apparent density, g/cc	2.6
Trace Element Analysis		Porosity, %	28
Iron (Fe), ppm	< 900	Absorption, %	15
Bismuth (Bi), ppm	< 1	Cristobalite content (after fire), %	2
Lead (Pb), ppm	< 25	Cristobalite content	6
Silver (Ag), ppm	< 25	(after 15 min. at 1390°C), %	· ·
Antimony (Sb), ppm	< 25	Leachability (30% boiling KOH, 30 g sample, 30 min), %	100
Tin (Sn), ppm	< 25		
Zinc (Zn), ppm	< 50	Core - Metal Reaction Compatibility	
1		Most nickel based, DS and SX alloys.	

Please note that all values quoted are based on test pieces and may vary according to component design. These values are not guaranteed in anyway whatsoever and should only be treated as indicative and for guidance only. Aug.12.2015